

Introduction

Eliflon C40-M00 fluoroelastomer is a medium viscosity copolymer of hexafluoropropene and vinylidene fluoride particularly suitable for injection moulding of sealing devices that must meet the most critical conditions of usage. The polymer is also appropriate for compression molding and extrusion applications. Due to narrow molecular weight distribution and a low long chain branching content Eliflon C40-M00 fluoroelastomer offers significant processing ease that can be modified when blended with similar fluoroelastomers. Eliflon C40-M00 is especially suited to curing with bisphenol-phosphonium salt systems.

Eliflon C40-M00 provides:

- improved injection rate
- fast curing rates
- low mould fouling
- easy mould release
- good mould flow
- improved extrusion
- good compression set resistance

Application

- Injection Moulded goods
- O rings
- Gaskets, seals and profiles
- Extruded cords

Safety and Handling

Despite the chemical inertness at ambient temperature, Eliflon C types fluoroelastomers should be handled in such a way to avoid contact with skin and eyes. In case of contact, wash thoroughly with soap and water. Store in a well ventilated place away from any source of heat. Smoking is strictly forbidden in working and storage areas. In the event of fire, toxic gases are produced. Refer to MSDS for additional information. For the safe handling of other compound ingredients normally used in fluoroelastomers compounding, please refer to the respective manufacturers.

Product Description

Chemical Composition	Copolymer of hexafluoropropene and vinylidene fluoride
Physical Form	Slabs
Color	Off white
Odor	Odorless
Specific Gravity	1,81 ± 0,02 g/cm ³
Fluorine Content	66 %
Glass transition temperature (Tg)	- 18 ± 1°C
Solubility	Low molecular weight esters and ketones
Storage Stability	Excellent
Mooney Viscosity, ML 1+10 at 121 °C (250 °F)	40 MU

Eliflon C40-M00 typical Compound

Eliflon C40-M00	91,8	phr
High activity magnesium oxide (MgO)	3	phr
Calcium Hydroxide (Ca(OH)₂)	6	phr
Medium Thermal Carbon Black (N990)	30	phr
Eliflon Curative 1¹	7,2	phr
Eliflon Curative 3²	1	phr
Processing aids (wax)	1	phr

1) Fluoroelastomer masterbatch 33% by weight of Bisphenol AF {4,4'-[2,2,2-trifluoro-1-(trifluoromethyl)ethylidene]bisphenol} and Benzyltriphenylphosphonium salt with 4,4'-[2,2,2-trifluoro-1-(trifluoromethyl)ethylidene]bisphenol (1:1)

2) Fluoroelastomer masterbatch 33% by weight of Benzyltriphenylphosphonium chloride

**IMPORTED
AND DISTRIBUTED BY**



Via Vittoria, 1
40068 San Lazzaro di Savena (BO) - Italy
Phone +39 (0) 51 6255442
E-mail info@sersar.net
www.sersar.net/

C40-M00



Performance of Eliflon C40-M00 in typical Compound

STOCK PROPERTIES

MDR at 180 °C, 6 min

ML	1,12	dN*m
T _{s2}	0,71	min
T _{c90}	1,49	min
MH	33,63	dN*m

Mechanical properties at 23°C, after aging in air 70 hrs at 250°C

100% modulus	5,0	MPa
Tensile strength	12,7	MPa
Elongation at the break	190	%
Hardness	75	ShoreA

Compression set, Method B disks, 25% def.

Aged 70 hr @ 200°C 17%

VULCANIZATE PROPERTIES

Slabs cured 10 min at 180°C, 110 kPa, post cured 3+18 hrs at 230°C

100% modulus	6,1	MPa
Tensile strength	13,1	MPa
Elongation at the break	220	%
Hardness	74	ShoreA

Swelling resistance in test fluids, Δ Volume %

Fuel C, 70 hr at 23°C	+ 3,5	%
Methanol (99%), 70 hr at 23°C	+ 75	%
IRM 903 Oil, 70 hr at 150°C	+ 2,0	%

Effect of filler [carbon black] level on Eliflon C40-M00 properties

	A	B	C	
Eliflon C40-M00	91,8	91,8	91,8	phr
High activity magnesium oxide (MgO)	3	3	3	phr
Calcium Hydroxide (Ca(OH) ₂)	6	6	6	phr
Medium Thermal Carbon Black (N990)	45	30	10	phr
Eliflon Curative 1 ¹	7,2	7,2	7,2	phr
Eliflon Curative 2 ²	1	1	1	phr
Processing aids (wax)	1	1	1	phr

1) Fluoroelastomer masterbatch 33% by weight of Bisphenol AF {4,4'-[2,2,2-trifluoro-1-(trifluoromethyl)ethylidene]bisphenol} and Benzyltriphenylphosphonium salt with 4,4'-[2,2,2-trifluoro-1-(trifluoromethyl)ethylidene]bisphenol (1:1)

2) Fluoroelastomer masterbatch 33% by weight of Benzyltriphenylphosphonium chloride

IMPORTED
AND DISTRIBUTED BY



Via Vittoria, 1
40068 San Lazzaro di Savena (BO) - Italy
Phone +39 (0) 51 6255442
E-mail info@sersar.net
www.sersar.net/

C40-M00



STOCK PROPERTIES

MDR at 180 °C, 6 min

	A	B	C	
ML	1,34	1,12	0,75	dN*m
T _s 2	0,62	0,71	1,42	min
T _c 90	1,38	1,49	2,44	min
MH	39,42	33,63	27,97	dN*m

VULCANIZATE PROPERTIES

Slabs cured 10 min at 180°C, 110 kPa, post cured 24 hrs at 230°C

	A	B	C	
100% modulus	10,0	6,1	2,6	MPa
Tensile strength	13,8	13,1	9,7	MPa
Elongation at the break	175	220	242	%
Hardness	84	74	59	ShoreA

Compression set, Method B disks, 25% def.

	A	B	C	
Aged 70 hr @ 200°C	21	17	13	%

Test procedures

Compression set	ASTM D 395, Method B	Mooney viscosity	ASTM D 1646
Compression set, O-ring	ASTM D 1414	Property change after oven heat aging	ASTM D 573
Hardness	ASTM D 2240, Durometer A (Shore A)	Stress strain properties	ASTM D 412
MDR (Moving Die Rheometer)	ASTM D 5289	Volume change in fluids	ASTM D 471

IMPORTED
AND DISTRIBUTED BY



Via Vittoria, 1
40068 San Lazzaro di Savena (BO) - Italy
Phone +39 (0) 51 6255442
E-mail info@sersar.net
www.sersar.net/

C40-M00



The information contained in these specifications is based on the technical data of Sersar Srl and is provided free of charge. It is to be used solely by skilled individuals who will observe all handling precautions given herein and the related documents referred to. The above information is provided with the understanding that skilled individuals who use the material described, alone or in a mixture with other materials, shall ensure that the particular conditions or the particular formulations adopted present no health or safety hazard.

Because conditions of product use or disposal are beyond our control, Sersar Srl issues no warranty, express or implied, and assumes no liability in connection with use of the information provided. The information contained herein is intended only as a guideline. An appropriate evaluation of any mixture of the material described above with other materials is absolutely necessary. The material described herein is not suitable for any implantation into the human body.

**IMPORTED
AND DISTRIBUTED BY**



Via Vittoria, 1
40068 San Lazzaro di Savena (BO) - Italy
Phone +39 (0) 51 6255442
E-mail info@sersar.net
www.sersar.net/